

Denka VINYKON W4023A PVC, W grade for equipment cords, for heat resistance

Category : Polymer , Thermoplastic , Vinyl (PVC)

Material Notes:

A PVC resin compound offering excellent physical properties and workability. A broad product lineup is available, including hard and soft grades, as well as those for extrusion and injection molding, etc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Denka-VINYKON-W4023A-PVC-W-grade-for-equipment-cords-for-heat-resistance.php

Physical Properties	Metric	English	Comments
Density	1.395 g/cc	0.05040 lb/in ³	JIS-Z-8807
Deformation	7.0 %	7.0 %	JIS-K-6723

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	91	91	JIS-K-6301
Tensile Strength at Break	20.601 MPa	2987.9 psi	JIS-K-6723
Elongation at Break	330 %	330 %	JIS-K-6723
100% Modulus	0.013734 GPa	1.9920 ksi	JIS-A-5756

Thermal Properties	Metric	English	Comments
Minimum Service Temperature, Air	-21.0 °C	-5.80 °F	JIS-K-6723

Electrical Properties	Metric	English	Comments
Volume Resistivity	7.00e+13 ohm-cm	7.00e+13 ohm-cm	JIS-K-6723
	@Temperature 60.0 °C	@Temperature 140 °F	
	9.00e+14 ohm-cm	9.00e+14 ohm-cm	JIS-K-6723
	@Temperature 30.0 °C	@Temperature 86.0 °F	

Descriptive Properties	Value	Comments
Heating: Retention Rate of Elongation, %	86	JIS-A-5756
Heating: Retention Rate of Tensile Strength, %	98	JIS-A-5756
Oil Resistance: Retention of Tensile Strength, %	92	JIS-K-6723
Oil Resistance: Retention Rate of Elongation, %	90	JIS-K-6723
Thermostability, min, JIS-K-6723	>240	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China