

Diamond Polymers ABS 7401 Injection Molding Grade, Extra High Impact

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Impact Grade, Molded

Material Notes:

Information Provided by Diamond Polymers, Inc. & Network Polymers, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Diamond-Polymers-ABS-7401-Injection-Molding-Grade-Extra-High-Impact.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ASTM D792
Linear Mold Shrinkage	0.0040 - 0.0060 cm/cm	0.0040 - 0.0060 in/in	ASTM D955
Melt Flow	1.7 g/10 min	1.7 g/10 min	ASTM D1238
	@Load 5.00 kg, Temperature 200 °C	@Load 11.0 lb, Temperature 392 °F	
	6.4 g/10 min	6.4 g/10 min	ASTM D1238
	@Load 3.80 kg, Temperature 230 °C	@Load 8.38 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	101	101	ASTM D785
Tensile Strength, Yield	44.1 MPa	6400 psi	chs 2 in/min; ASTM D638
Flexural Modulus	1.964 GPa	284.9 ksi	tangent; chs 0.05 in/min; ASTM D790
Izod Impact, Notched	3.84 J/cm	7.19 ft-lb/in	ASTM D256
	@Thickness 3.17 mm, Temperature 23.0 °C	@Thickness 0.125 in, Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Vicat Softening Point	103 °C	217 °F	ASTM D1525
	@Load 1.00 kg, Thickness 3.17 mm	@Load 2.20 lb, Thickness 0.125 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China