

Domo 2448L Polypropylene Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

Material Notes:

Information provided by Domo.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Domo-2448L-Polypropylene-Copolymer.php

Physical Properties	Metric	English	Comments
Density	0.910 g/cc	0.0329 lb/in ³	ISO 1183
Melt Flow	6.0 g/10 min	6.0 g/10 min	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Modulus	1.15 GPa	167 ksi	ISO 527-2
Izod Impact, Notched (ISO)	5.00 kJ/m ²	2.38 ft-lb/in ²	ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	6.00 kJ/m ²	2.86 ft-lb/in ²	ISO 180/1A
	@Temperature -20.0 °C	@Temperature -4.00 °F	
	7.00 kJ/m ²	3.33 ft-lb/in ²	ISO 180/1A
	@Temperature 0.000 °C	@Temperature 32.0 °F	
	15.0 kJ/m ²	7.14 ft-lb/in ²	ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	163 °C	325 °F	ISO 3146
Vicat Softening Point	63.0 °C	145 °F	B50 (50N); ISO 306
	150 °C	302 °F	A50 (10N); ISO 306

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China