

Dow Corning 3-0110 AUTOMOTIVE SEALANT

Category : Polymer , Adhesive , Thermoset , Silicone , Silicone, RTV, Adhesive/Sealant Grade

Material Notes:

One-part, alkoxy-cure, room temperature vulcanizing (RTV) temperature-silicone sealant Information provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-3-0110-AUTOMOTIVE-SEALANT.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.30 g/cc	1.30 g/cc	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	47	47	
Tensile Strength, Ultimate	2.76 MPa	400 psi	
Elongation at Break	375 %	375 %	
Shear Strength	1.95 MPa	283 psi	

Processing Properties	Metric	English	Comments
Cure Time	1440 min	24.0 hour	
	@Temperature 22.0 °C	@Temperature 71.6 °F	
Shelf Life	18.0 Month	18.0 Month	

Descriptive Properties	Value	Comments
Color	grey	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China