

## Dow Corning C6-530 LIQUID SILICONE RUBBER KIT

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone Rubber

### Material Notes:

Dow Corning® Class VI Elastomers are heat cured elastomer raw materials for use by customers fabricating medical devices and parts  
Information provided by Dow Corning

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Dow-Corning-C6-530-LIQUID-SILICONE-RUBBER-KIT.php](http://www.lookpolymers.com/polymer_Dow-Corning-C6-530-LIQUID-SILICONE-RUBBER-KIT.php)

| Mechanical Properties      | Metric    | English  | Comments |
|----------------------------|-----------|----------|----------|
| Hardness, Shore A          | 30        | 30       |          |
| Tensile Strength, Ultimate | 8.20 MPa  | 1190 psi |          |
| Elongation at Break        | 830 %     | 830 %    |          |
| Tear Strength              | 28.0 kN/m | 160 pli  |          |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China