

Dow Corning C6-540 LIQUID SILICONE RUBBER KIT

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone Rubber

Material Notes:

Dow Corning® Class VI Elastomers are heat cured elastomer raw materials for use by customers fabricating medical devices and parts. Information provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-C6-540-LIQUID-SILICONE-RUBBER-KIT.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	40	40	
Tensile Strength, Ultimate	8.89 MPa	1290 psi	
Elongation at Break	740 %	740 %	
Tear Strength	42.1 kN/m	240 pli	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China