

## Dow Corning MOLYKOTE® 55 O-RING GREASE

Category : Fluid , Lubricant , Silicone Base

### Material Notes:

Phenyl-methyl silicone grease formulated for O-ringsInformation provided by Dow Corning

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Dow-Corning-MOLYKOTE-55-O-RING-GREASE.php](http://www.lookpolymers.com/polymer_Dow-Corning-MOLYKOTE-55-O-RING-GREASE.php)

| Physical Properties | Metric               | English              | Comments |
|---------------------|----------------------|----------------------|----------|
| Specific Gravity    | 0.960 g/cc           | 0.960 g/cc           |          |
|                     | @Temperature 25.0 °C | @Temperature 77.0 °F |          |
| Kinematic Viscosity | 100 cSt              | 100 cSt              |          |

| Mechanical Properties      | Metric | English | Comments |
|----------------------------|--------|---------|----------|
| Penetration P(60), 1/10 mm | 290    | 290     |          |

| Thermal Properties               | Metric   | English  | Comments |
|----------------------------------|----------|----------|----------|
| Maximum Service Temperature, Air | 175 °C   | 347 °F   |          |
| Minimum Service Temperature, Air | -65.0 °C | -85.0 °F |          |
| Dropping Point                   | 220 °C   | 428 °F   |          |

| Processing Properties | Metric     | English    | Comments |
|-----------------------|------------|------------|----------|
| Shelf Life            | 60.0 Month | 60.0 Month |          |

| Descriptive Properties | Value | Comments |
|------------------------|-------|----------|
| Color                  | white |          |
| NLGI Number            | 2     |          |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China