

Dow Corning MOLYKOTE® G-0010 GREASE

Category : Fluid , Lubricant

Material Notes:

Polyurea-thickened mineral oil greaseInformation provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-MOLYKOTE-G-0010-GREASE.php

Physical Properties	Metric	English	Comments
Kinematic Viscosity	125 cSt	125 cSt	

Mechanical Properties	Metric	English	Comments
Four Ball Extreme Pressure, Weld Load	314.9 kg	694.4 lb (mass)	
Penetration P(60), 1/10 mm	265 - 295	265 - 295	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	170 °C	338 °F	
Minimum Service Temperature, Air	0.300 °C	32.5 °F	
Dropping Point	>= 260 °C	>= 500 °F	

Processing Properties	Metric	English	Comments
Shelf Life	60.0 Month	60.0 Month	

Descriptive Properties	Value	Comments
Color	green	
NLGI Number	2	
Thickening System	polyurea	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China