

Dow Corning OE-6450

Category : Polymer , Adhesive , Thermoset , Silicone

Material Notes:

Two-part, solvent-less, high purity and heat cure type semiconductor protective coating of silicone Information provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-OE-6450.php

Physical Properties	Metric	English	Comments
Viscosity	1175 cP	1175 cP	dynamic, Part B
	1750 cP	1750 cP	dynamic
	2575 cP	2575 cP	dynamic, Part A

Mechanical Properties	Metric	English	Comments
Penetration P(0), 1/10 mm	45	45	
Penetration P(60), 1/10 mm	45	45	

Optical Properties	Metric	English	Comments
Refractive Index	1.54	1.54	

Processing Properties	Metric	English	Comments
Cure Time	60.0 min	1.00 hour	
	@Temperature 100 °C	@Temperature 212 °F	
	1440 min	24.0 hour	
	@Temperature 22.0 °C	@Temperature 71.6 °F	
Shelf Life	12.0 Month	12.0 Month	

Descriptive Properties	Value	Comments
Working Time (min)	240	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China