

Dow Corning SE 1886 KIT

Category : Polymer , Adhesive , Thermoset , Silicone

Material Notes:

Two-part, clear, 1:1, addition cure, low viscosity, good working time. Information provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-SE-1886-KIT.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.980 g/cc	0.980 g/cc	
	@Temperature 25.0 °C	@Temperature 77.0 °F	
Viscosity	1100 cP	1100 cP	dynamic

Mechanical Properties	Metric	English	Comments
Penetration P(60), 1/10 mm	50	50	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	150 °C	302 °F	
Minimum Service Temperature, Air	-45.0 °C	-49.0 °F	

Electrical Properties	Metric	English	Comments
Dielectric Constant	2.7	2.7	
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Dielectric Strength	18.0 kV/mm	457 kV/in	

Processing Properties	Metric	English	Comments
Cure Time	60.0 min	1.00 hour	
	@Temperature 130 °C	@Temperature 266 °F	
Shelf Life	17.0 Month	17.0 Month	

Descriptive Properties	Value	Comments
Appearance	clear	
Flowable	yes	
Gel Hardness (Grams/Penetration)	105	

Descriptive Properties	Value	Comments
Self Leveling	yes	
Water Resistant	yes	
Working Time (min)	180	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China