

Dow Corning SILASTIC® 9252/250P PARTS A&B

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone Rubber

Material Notes:

Information provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-SILASTIC-9252250P-PARTS-AB.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.09 g/cc	1.09 g/cc	
	@Temperature 25.0 °C	@Temperature 77.0 °F	
Solids Content	100 %	100 %	
Viscosity	25000 cP	25000 cP	mixing, dynamic

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	5.00 MPa	725 psi	
Elongation at Break	450 %	450 %	
Tear Strength	7.01 kN/m	40.0 pli	

Electrical Properties	Metric	English	Comments
Volume Resistivity	4.80e+15 ohm-cm	4.80e+15 ohm-cm	

Processing Properties	Metric	English	Comments
Pot Life	4320 min	4320 min	
Shelf Life	15.0 Month	15.0 Month	

Descriptive Properties	Value	Comments
Appearance	translucent	
Gel Hardness (Grams/Penetration)	33	
Mix Ratio (X:1)	10	Base to Catalyst

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China