

Dow Corning SILASTIC® 9252/900P PARTS A&B

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone Rubber

Material Notes:

Information provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-SILASTIC-9252900P-PARTS-AB.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.13 g/cc	1.13 g/cc	
	@Temperature 25.0 °C	@Temperature 77.0 °F	
Solids Content	100 %	100 %	
Viscosity	90000 cP	90000 cP	mixing, dynamic

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	37	37	
Tensile Strength, Ultimate	6.62 MPa	960 psi	
Elongation at Break	500 %	500 %	
Tear Strength	14.0 kN/m	80.0 pli	

Electrical Properties	Metric	English	Comments
Volume Resistivity	3.40e+15 ohm-cm	3.40e+15 ohm-cm	

Processing Properties	Metric	English	Comments
Pot Life	4320 min	4320 min	
Shelf Life	15.0 Month	15.0 Month	

Descriptive Properties	Value	Comments
Appearance	translucent	
Mix Ratio (X:1)	100	Base to Catalyst ETN

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China