

Dow Corning SILASTIC® 9412/30E KIT PARTS A&B

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone Rubber

Material Notes:

30 Durometer, 2-part, 1 to 1 mix, 2-part, 1 to 1 mix, opaque, Auto connector seal grade, Liquid Silicone Rubber. Information provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-SILASTIC-941230E-KIT-PARTS-AB.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.12 g/cc	1.12 g/cc	
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	30	30	
Tensile Strength, Ultimate	8.000 MPa	1160 psi	
Elongation at Break	800 %	800 %	
Tear Strength	20.025 kN/m	114.23 pli	
Compression Set	18 %	18 %	

Processing Properties	Metric	English	Comments
Pot Life	4320 min	4320 min	
Shelf Life	15.0 Month	15.0 Month	

Descriptive Properties	Value	Comments
Appearance	opaque	
Mix Ratio (X:1)	100	Base to Catalyst ETN
Water Resistant	yes	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China