

Dow Corning SILASTIC® LC-30-2004 PART A&B KIT

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone Rubber

Material Notes:

30 Durometer, 2 parts, 1 to 1 mix, translucent, FDA 21 CFR 177.2600 and BfR, XV, molding and injection molding grade Liquid Silicone Rubber. Information provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-SILASTIC-LC-30-2004-PART-AB-KIT.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.119 g/cc	1.119 g/cc	
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	30.9	30.9	
Tensile Strength, Ultimate	7.274 MPa	1055 psi	
Elongation at Break	940 %	940 %	
Tear Strength	19.5 kN/m	111 pli	
Compression Set	18.9 %	18.9 %	

Processing Properties	Metric	English	Comments
Shelf Life	6.00 Month	6.00 Month	

Descriptive Properties	Value	Comments
Appearance	translucent	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China