

Dow Corning SILASTIC® LCS-740 SILICONE RUBBER

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone Rubber

Material Notes:

40 Durometer, translucent, low compression set, uncatalysed Silicone Rubber Base suitable for molding. Information provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-SILASTIC-LCS-740-SILICONE-RUBBER.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.09 g/cc	1.09 g/cc	
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	45	45	
Tensile Strength, Ultimate	4.55 MPa	660 psi	
Tensile Strength, Yield	1.07 MPa	155 psi	at 150% Elongation, maximum
Elongation at Break	345 %	345 %	
Tear Strength	7.01 kN/m	40.0 pli	
Compression Set	8.0 %	8.0 %	

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-73.0 °C	-99.4 °F	

Processing Properties	Metric	English	Comments
Shelf Life	36.0 Month	36.0 Month	

Descriptive Properties	Value	Comments
Appearance	translucent	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China