

Dow Corning XIAMETER® PMCPPMX-200 60,000CS Silicone Fluid

Category : Fluid

Material Notes:

Is chemically equivalent to DOW CORNING® 200 FLUID 60,000CS. 100% active, 60,000 cSt, polydimethylsiloxane polymer. Information provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-XIAMETER-PMCPPMX-200-60000CS-Silicone-Fluid.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.976 g/cc	0.976 g/cc	
	@Temperature 25.0 °C	@Temperature 77.0 °F	
Viscosity Measure	60000 cSt	60000 cSt	Kinetic/Kinematic
Surface Tension	21.5 dynes/cm	21.5 dynes/cm	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	200 °C	392 °F	
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	
Pour Point	-41.0 °C	-41.8 °F	
Flash Point	>= 100 °C	>= 212 °F	Closed Cup
	>= 321 °C	>= 610 °F	Open Cup

Optical Properties	Metric	English	Comments
Refractive Index	1.403	1.403	

Processing Properties	Metric	English	Comments
Shelf Life	36.0 Month	36.0 Month	

Descriptive Properties	Value	Comments
Hydrophobic	Yes	
Water Dispersible	Yes	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China