

## **Dow Latex XZ 92229.00 Experimental Latex**

Category: Polymer, Thermoplastic, Styrene-Butadiene

## **Material Notes:**

Description: XZ 92229.00 Experimental latex is an aqueous dispersion of a modified carboxylated styrene butadiene copolymer. It has been developed for use as a secondary backing latex for tufted carpet where a soft handle is required. Applications: Precoating and Secondary backing Information provided by Styron

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Dow-Latex-XZ-9222900-Experimental-Latex.php

Physical Properties	Metric	English	Comments
Solids Content	51.5 - 52.5 %	51.5 - 52.5 %	
Particle Mesh Size	100 Mesh	100 Mesh	<0.1 g/l residues
	325 Mesh	325 Mesh	<0.2 g/l residues
pH	7.7 - 8.3	7.7 - 8.3	
Brookfield Viscosity	<= 300 cP	<= 300 cP	#2 @ 50 rpm
Surface Tension	40 - 50 dynes/cm	40 - 50 dynes/cm	

Descriptive Properties	Value	Comments
Minimum film formation temperature	<0°C	
Styrene content in polymer	0.525	

## Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China