

Dow Retain® ABS 7342 ABS

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

Material Notes:

Data provided by Dow Chemical.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Retain-ABS-7342-ABS.php

Physical Properties	Metric	English	Comments
Density	1.06 g/cc	0.0383 lb/in ³	ASTM Data
Melt Flow	5.7 g/10 min @Load 3.80 kg, Temperature 230 °C	5.7 g/10 min @Load 8.38 lb, Temperature 446 °F	ASTM Data

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	36.0 MPa	5220 psi	ASTM Data
Tensile Modulus	2.02 GPa	293 ksi	ASTM Data
Izod Impact, Notched	1.39 J/cm	2.60 ft-lb/in	ASTM Data

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	87.0 °C	189 °F	Unannealed; ASTM Data
Deflection Temperature at 1.8 MPa (264 psi)	74.0 °C	165 °F	Unannealed; ASTM Data
Vicat Softening Point	105 °C	221 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China