

DuPont Bexloy® AXW602NC010 3% Glass Reinforced, Heat Stabilized Modified Ionomer Resin (discontinued **)

Category : Polymer , Thermoplastic , Ionomer , Ionomer, Molded

Material Notes:

A 3% glass reinforced, heat stabilized modified ionomer resin engineered for injection molded interior automotive applications. Availability: North America Information provided by DuPont.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DuPont-Bexloy-AXW602NC010-3-Glass-Reinforced-Heat-Stabilized-Modified-Ionomer-Resin-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.970 g/cc	0.0350 lb/in ³	ASTM D792 - ISO 1183
Linear Mold Shrinkage, Flow	0.0075 cm/cm	0.0075 in/in	ASTM D955
Melt Flow	1.5 g/10 min @Load 2.16 kg, Temperature 190 °C	1.5 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238 - ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	22.1 MPa	3200 psi	ASTM D638 - ISO 527-2
Elongation at Break	400 %	400 %	ASTM D638 - ISO 527-2
Flexural Modulus	0.7580 GPa	109.9 ksi	ASTM D790
Izod Impact, Notched	8.54 J/cm @Temperature -30.0 °C	16.0 ft-lb/in @Temperature -22.0 °F	ASTM D256
Gardner Impact	36.2 J @Temperature -30.0 °C	26.7 ft-lb @Temperature -22.0 °F	ASTM D3029
Impact Test	18.0 J @Temperature -30.0 °C	13.2 ft-lb @Temperature -22.0 °F	Rheometric, 5mph, 1/2" diameter tup, 3" diameter ring
	21.9 J @Temperature 22.8 °C	16.2 ft-lb @Temperature 73.0 °F	Rheometric, 5mph, 1/2" diameter tup, 3" diameter ring

Thermal Properties	Metric	English	Comments
CTE, linear	76.0 µm/m-°C @Temperature -30.0 - 80.0 °C	42.2 µin/in-°F @Temperature -22.0 - 176 °F	ASTM E831
Deflection Temperature at 0.46 MPa	80.0 °C	176 °F	

(56 psi) Thermal Properties	Metric	English	ASTM D648 Comments
Deflection Temperature at 1.8 MPa (264 psi)	48.3 °C	119 °F	ASTM D648

Processing Properties	Metric	English	Comments
Nozzle Temperature	238 - 271 °C	460 - 520 °F	
Melt Temperature	238 - 288 °C	460 - 550 °F	
Mold Temperature	15.6 - 60.0 °C	60.0 - 140 °F	
Drying Temperature	60.0 - 79.4 °C	140 - 175 °F	
Moisture Content	<= 0.080 %	<= 0.080 %	
Back Pressure	>= 0.345 MPa	>= 50.0 psi	no units given

Descriptive Properties	Value	Comments
Injection Speed	Fast	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China