

DuPont Elvaloy® 3717 AC Ethylene and 17% Butyl Acrylate Copolymer

Category : Polymer , Film , Thermoplastic , Ethylene Butyl Acrylate

Material Notes:

Elvaloy® 3717 AC can be used for coextrusion, compounding and injection molding. In coextrusion, it can be used to improve sealing; in compounding, to improve low temperature and impact properties. Elvaloy® 3717 AC also is very suitable as a carrier polymer in masterbatches. Elvaloy® 3717 AC is easily processed on standard equipment used for low density polyethylene. Information provided by DuPont.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DuPont-Elvaloy-3717-AC-Ethylene-and-17-Butyl-Acrylate-Copolymer.php

Physical Properties	Metric	English	Comments
Density	0.924 g/cc	0.0334 lb/in ³	ASTM D792 - ISO 1183
Melt Flow	7.0 g/10 min @Load 2.16 kg, Temperature 190 °C	7.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238 - ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	89	89	ASTM D2240 - ISO 868
Hardness, Shore D	31	31	ASTM D2240 - ISO 868
Tensile Strength at Break	10.0 MPa	1450 psi	500 mm/min; ASTM D638 - ISO 527-2
Elongation at Break	850 %	850 %	500 mm/min; ASTM D638 - ISO 527-2
Tensile Modulus	0.0400 GPa	5.80 ksi	1 mm/min; ASTM D638 - ISO 527-2

Thermal Properties	Metric	English	Comments
Melting Point	96.0 °C	205 °F	By DSC; ASTM D3418 - ISO 3146
Vicat Softening Point	55.0 °C	131 °F	A₅₀ (10N); ASTM D1525 - ISO 306

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	150 °C	302 °F	Extrusion lamination and extrusion coating
	150 °C	302 °F	Cast film
	150 °C	302 °F	Blown film
Middle Barrel Temperature	160 °C	320 °F	Blown film
	210 °C	410 °F	Cast film

Processing Properties	Metric 220 °C	English 428 °F	Comments Extrusion lamination
Front Barrel Temperature	170 °C	338 °F	Blown film
	250 °C	482 °F	Cast film
	290 °C	554 °F	Extrusion lamination
Adapter Temperature	180 °C	356 °F	Blown film
	250 °C	482 °F	Cast Film
	290 °C	554 °F	Extrusion lamination
Die Temperature	180 °C	356 °F	Blown film
	250 °C	482 °F	Cast film
	290 °C	554 °F	Extrusion lamination

Descriptive Properties	Value	Comments
BA-Content	17 wt. %	DuPont Method

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China