

## DuPont Fusabond® MN493D Ethylene Octene Copolymer (discontinued \*\*)

Category : Other Engineering Material , Additive/Filler for Polymer , Polymer , Thermoplastic , Elastomer, TPE

### Material Notes:

Typical Use: Nylon 6 toughenerNylon 6/6 toughenerComplies to FDA 21CFR 175.105Availability: North AmericaInformation provided by DuPont.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_DuPont-Fusabond-MN493D-Ethylene-Octene-Copolymer-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_DuPont-Fusabond-MN493D-Ethylene-Octene-Copolymer-nbspdiscontinued-.php)

| Physical Properties | Metric       | English       | Comments |
|---------------------|--------------|---------------|----------|
| Density             | 0.870 g/cc   | 0.0314 lb/in³ |          |
| Melt Flow           | 1.6 g/10 min | 1.6 g/10 min  |          |

| Thermal Properties | Metric  | English | Comments |
|--------------------|---------|---------|----------|
| Melting Point      | 48.0 °C | 118 °F  |          |

| Descriptive Properties | Value  | Comments      |
|------------------------|--------|---------------|
| MAH Graft Level, wt%   | Medium | FTIR (DuPont) |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China