

DuPont™ Kapton® 200VN Polyimide Film, 50 Micron Thickness

Category : Polymer , Film , Thermoset , Polyimide, TS , Polyimide, Thermoset Film

Material Notes:

Film thickness 50 micron 2.0 mil)All purpose polyimide film. Can be laminated, diecut, slit, formed, or adhesive-coated. Similar to Kapton® Type HN with added dimensional stability. Available in thicknesses from 0.3 mil (7.5 µm) to 5 mil (125 µm).General Kapton® information: Kapton® is synthesized by polymerizing an aromatic dianhydride with an aromatic diamine. It has excellent chemical resistance; there are no known organic solvents for the film. It does not melt. It can be used at both high and low temperature extremes. Kapton® polyimide films can be used in a variety of electrical and electronic uses: wire and cable tapes, formed coil insulation, substrates for printed circuit boards, motor slot liners, magnet wire insulation, transformer and capacitor insulation, magnetic and pressure-sensitive tapes, and tubing.Data provided by DuPont High Performance Films.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DuPont-Kapton-200VN-Polyimide-Film-50-Micron-Thickness.php

Physical Properties	Metric	English	Comments
Density	1.42 g/cc	0.0513 lb/in³	
Water Absorption	2.8 %	2.8 %	24 hr/23°C. ASTM D570
Moisture Absorption at Equilibrium	1.8 %	1.8 %	50% RH; 23°C

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	75 %	75 %	Orientation not specified; ASTM D882
Poissons Ratio	0.34	0.34	Value for Kapton® HN
Secant Modulus	2.80 GPa	406 ksi	ASTM D882
Coefficient of Friction, Dynamic	0.48	0.48	Value for Kapton® HN. Film to film. ASTM D1894-90
Coefficient of Friction, Static	0.63	0.63	Value for Kapton® HN. Film to film. ASTM D1894-90
Film Tensile Strength at Break, MD	221 MPa	32100 psi	Orientation not specified; ASTM D882

Thermal Properties	Metric	English	Comments
CTE, linear	20.0 µm/m-°C	11.1 µin/in-°F	Value for Kapton® HN
	@Temperature 20.0 °C	@Temperature 68.0 °F	
	32.0 µm/m-°C	17.8 µin/in-°F	Value for Kapton® HN
	@Temperature 100 °C	@Temperature 212 °F	
	40.0 µm/m-°C	22.2 µin/in-°F	Value for Kapton® HN
	@Temperature 250 °C	@Temperature 482 °F	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.120 W/m-K	0.833 BTU-in/hr-ft ² -°F	Value for Kapton® HN
Maximum Service Temperature, Air	400 °C	752 °F	Kapton® can function after brief exposure to 400°C (750°F). Various grades are UL rated for continuous service at 220-240°C (430-460°F).
Minimum Service Temperature, Air	-269 °C	-452 °F	Maintains properties and flexibility
Glass Transition Temp, Tg	385 °C	725 °F	Value for Kapton® HN
Flammability, UL94	V-0	V-0	
Oxygen Index	43 %	43 %	ASTM D2863-87

Optical Properties	Metric	English	Comments
Refractive Index	1.70 @Wavelength 589.3 nm	1.70 @Wavelength 589.3 nm	Value for Kapton® HN. Na D line; ASTM D542-90

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+10 ohm-cm	1.00e+10 ohm-cm	in damp heat; IPC-TM-650; Method 2.5.17
	1.50e+17 ohm-cm	1.50e+17 ohm-cm	per ASTM D257-91
Dielectric Constant	3.6 @Frequency 1000 Hz	3.6 @Frequency 1000 Hz	Use evaporated metal electrodes, two terminal system of measurement at standard conditions.; ASTM D150
Dielectric Strength	217 kV/mm	5510 kV/in	Flat sheets in air placed between 1/4 in diameter brass electrodes with 0.8 mm (1/32 in) edge radius subjected to 60 cycles AC voltage at 600V/s rate of rise to the breakdown voltage.; ASTM D149-81
Dissipation Factor	0.0020 @Frequency 1000 Hz	0.0020 @Frequency 1000 Hz	Same test as dielectric constant.

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China