

DuPont™ Nomex® 410 Paper, 7 mil Nominal Thickness

Category : Other Engineering Material , Composite Fibers , Polymer , Film , Thermoset , Aramid

Material Notes:

Nomex® Type 410 is a calendared insulation paper which offers high inherent dielectric strength, mechanical toughness, flexibility, and resilience. It is the original form of Nomex® paper and is widely used in a majority of electrical applications. General NOMEX Information: Nomex® is a family of aromatic polyamide (aramid) fibers. This family consists of staple fibers, continuous filament yarns, paper, and spunlaced fabrics. The paper is produced from two forms of the aramid polymer. Small fibrous binder particles (fibrils) derived directly from the polymer under high shear conditions are mixed with short fibers (floc) which are cut to length from a fiber filament. The floc and fibrils are combined in a water based slurry from which a continuous sheet is produced on a specialized papermaking machine. This initial paper (as in Type 411) is low density and has poor properties. Subsequent densification and internal bonding is achieved by high temperature calendaring. The resulting paper is mechanically strong and has good electrical properties. Some uses for paper product include insulation in electric motors and transformers, wire wrapping, and honeycombed strength members in many aircraft. Nomex® brand fibers are inherently flame resistant: the flame resistance is a polymer property and does not diminish with the life of the fiber. Nomex® meta-aramid, poly(meta-phenyleneisophthalamide), is prepared from meta-phenylenediamine and isophthaloyl chloride in an amide solvent. It is a long chain polyamide in which at least 85% of the amide linkages are attached directly to two aromatic rings. The meta oriented phenylene forms bends in the polymer chain, reducing chain rigidity as compared to the para orientation in the chemically similar Kevlar® chain. This flexible polymer chain gives Nomex® more textile-like qualities while retaining high temperature properties similar to Kevlar®. Information provided by DuPont.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DuPont-Nomex-410-Paper-7-mil-Nominal-Thickness.php

Physical Properties	Metric	English	Comments
Bulk Density	0.950 g/cc	0.0343 lb/in³	
Density	0.950 g/cc	0.0343 lb/in³	
Thickness	178 microns	7.00 mil	Nominal
	183 microns	7.20 mil	Typical; ASTM D374

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	18 %	18 %	ASTM D828
Film Elongation at Break, TD	14 %	14 %	ASTM D828
Tear Strength, Total	27.0 N	6.07 lb (f)	Initial in TD; ASTM D1004
	50.0 N	11.2 lb (f)	Initial in MD; ASTM D1004
Elmendorf Tear Strength, MD	2.17 g/micron	55.0 g/mil	Calculated from mfr's report of 3.9 N per TAPPI-414 and the typical thickness
			Calculated from mfr's report of

Elmendorf Tear Strength, TD Mechanical Properties	4.13 g/micron Metric	105 g/mil English	7.4 N per TAPPI-414 and the typical thickness Comments
Film Tensile Strength at Break, MD	119.8 MPa	17380 psi	Calculated from mfr's report of 219 N/cm per ASTM D828 and the typical thickness
Film Tensile Strength at Break, TD	60.7 MPa	8800 psi	Calculated from mfr's report of 111 N/cm per ASTM D828 and the typical thickness

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.143 W/m-K @Temperature 150 °C	0.992 BTU-in/hr-ft²-°F @Temperature 302 °F	
Maximum Service Temperature, Air	220 °C	428 °F	220°C insulation by UL, the US Navy, and other tests
Oxygen Index	27 - 32 %	27 - 32 %	Range at RT for Type 410; depends on thickness and density
Shrinkage, MD	0.60 %	0.60 %	at 300°C
Shrinkage, TD	0.20 %	0.20 %	at 300°C

Electrical Properties	Metric	English	Comments
Volume Resistivity	2.00e+16 ohm-cm	2.00e+16 ohm-cm	50% RH; tested on 10 mil thickness sample; ASTM D257
Surface Resistivity per Square	2.00e+16 ohm	2.00e+16 ohm	tested on 10 mil thickness sample; ASTM D257
Dielectric Constant	2.7 @Frequency 60 Hz	2.7 @Frequency 60 Hz	ASTM D150
Dielectric Strength	33.0 kV/mm	838 kV/in	AC Rapid Rise; ASTM D149
	55.0 kV/mm	1400 kV/in	Full-wave Impulse; ASTM D3426
Dissipation Factor	0.0060 @Frequency 60 Hz	0.0060 @Frequency 60 Hz	ASTM D150

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China