

DuPont Nucrel® 960 Ethylene-Methacrylic Acid Copolymer Resin

Category : Polymer , Thermoplastic , Ethylene Methyl Acrylate

Material Notes:

Nucrel® 599 is a tough, lightweight, easily processed ethylene copolymer resin. This resin is inherently flexible without the need for plasticizers. The resin can be pigmented, UV-stabilized for exterior applications and painted or plated for special decorative effects. Typical Applications: Heat sealable coatingCarrier resin for color concentratesMetal coatingDispersionsGlass coatingFeatures: Good adhesion to metal and polar substratesGood flow characteristics for compounding applicationsMay be processed into a dispersion through standard dispersion techniquesAllows high pigment loadings for concentratesInformation provided by DuPont.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DuPont-Nucrel-960-Ethylene-Methacrylic-Acid-Copolymer-Resin.php

Physical Properties	Metric	English	Comments
Density	0.940 g/cc	0.0340 lb/in ³	ASTM D792
Melt Index of Compound	60 g/10 min @Load 2.16 kg, Temperature 190 °C	60 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	46	46	Initial (peak) hardness; ASTM D2240
Tensile Strength at Break	21.4 MPa	3100 psi	Type IV specimen, compression molded, crosshead speed 2 in/min; ASTM D638
Elongation at Break	540 %	540 %	Type IV specimen, compression molded, crosshead speed 2 in/min; ASTM D638
Flexural Modulus	0.0551 GPa	7.99 ksi	ASTM D790
Izod Impact, Notched	NB	NB	ASTM D256
Tensile Impact Strength	606 kJ/m ²	288 ft-lb/in ²	At 23°C; ASTM D1822S
	342 kJ/m ² @Temperature -40.0 °C	163 ft-lb/in ² @Temperature -40.0 °F	ASTM D1822S

Thermal Properties	Metric	English	Comments
Melting Point	73.0 - 91.0 °C	163 - 196 °F	ASTM D3418(DSC)
Vicat Softening Point	62.0 °C	144 °F	ASTM D1525

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Zone 1 Processing Properties	160 °C Metric	320 °F English	Comments
Zone 2	182 °C	360 °F	
Zone 3	193 °C	379 °F	
Zone 4	204 °C	399 °F	
Zone 5	204 °C	399 °F	
Die Temperature	204 °C	400 °F	
Melt Temperature	149 - 232 °C	300 - 450 °F	

Descriptive Properties	Value	Comments
Methacrylic Acid Content	15 wt. %	DuPont Method

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China