

DuPont Performance Polymers Crastin® LW9330 BK851 PBT+SAN (Unverified Data)**

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , SAN Polymer , Styrene Acrylonitrile (SAN), Molded, Glass Reinforced

Material Notes:

30% Glass Reinforced Polybutylene Terephthalate Blend with Low Warpage Characteristics Crastin LW9330 BK851 is a 30% glass fiber reinforced black polybutylene terephthalate blend for injection molding. It has improved surface aesthetics excellent dimenInformation provided by DuPont Performance Polymers

Order this product through the following link:
http://www.lookpolymers.com/polymer_DuPont-Performance-Polymers-Crastin-LW9330-BK851-PBTSAN-nbspUnverified-Data.php

Physical Properties	Metric	English	Comments
Density	1.42 g/cc	0.0513 lb/in³	ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	133 MPa	19300 psi	ISO 527-1/-2
Elongation at Break	2.2 %	2.2 %	ISO 527-1/-2
Tensile Modulus	9.60 GPa	1390 ksi	ISO 527-1/-2
Izod Impact, Notched (ISO)	7.00 kJ/m²	3.33 ft-lb/in²	ISO 180/1A
Charpy Impact Unnotched	5.00 J/cm²	23.8 ft-lb/in²	ISO 179/1eU
Charpy Impact, Notched	0.800 J/cm²	3.81 ft-lb/in²	ISO 179/1eA

Thermal Properties	Metric	English	Comments
Melting Point	225 °C	437 °F	10°C/min; ISO 11357-1/-3
Flammability, UL94	HB @Thickness 0.800 mm	HB @Thickness 0.0315 in	IEC 60695-11-10
Flame Spread	32 mm/min @Thickness 1.00 mm	1.3 in/min @Thickness 0.0394 in	ISO 3795 (FMVSS 302)

Descriptive Properties	Value	Comments
Part Marking Code	>PBT+SAN-GF30<	ISO 11469
Processing	Injection Moulding	
Regional Availability	Asia Pacific	

Descriptive Properties	Europe Value	Comments
	Global	
	Near East/Africa	
	North America	
	South and Central America	
Resin Identification	PBT+SAN-GF30	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China