

## DuPont Performance Polymers Neoprene 842A Polychloroprene

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Chlorosulfonated Polyethylene Rubber

### Material Notes:

DuPont™ Neoprene 842A liquid dispersion contains a medium modulus polychloroprene homopolymer made in an anionic colloidal system.

Main Feature - This liquid dispersion gives medium strength cured films having a slow crystallization rate. Suggested End Uses Bonded batts Impregnated paper Dipped goods Laminating adhesives Industrial coatings Elasticized aluminous cement

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_DuPont-Performance-Polymers-Neoprene-842A-Polychloroprene.php](http://www.lookpolymers.com/polymer_DuPont-Performance-Polymers-Neoprene-842A-Polychloroprene.php)

| Physical Properties | Metric               | English              | Comments          |
|---------------------|----------------------|----------------------|-------------------|
| Specific Gravity    | 1.11 g/cc            | 1.11 g/cc            | Liquid Dispersion |
|                     | 1.23 g/cc            | 1.23 g/cc            | Polymer           |
| Solids Content      | 50 %                 | 50 %                 |                   |
| pH                  | >= 12                | >= 12                |                   |
|                     | @Temperature 25.0 °C | @Temperature 77.0 °F |                   |

| Descriptive Properties | Value              | Comments |
|------------------------|--------------------|----------|
| Electrolyte Stability  | Good               |          |
| Emulsifying Agent      | Potassium Rosinate |          |
| Freeze/Thaw Stability  | Not stable         |          |
| Mechanical Stability   | Good               |          |
| Storage Stability      | Fairly good        |          |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China