

DuPont Performance Polymers Zytel® HTN 54G35EF BKB336 Polyphthalamide (PPA) (Unverified Data)**

Category : Polymer , Thermoplastic , Polyphthalamide (PPA) , Polyphthalamide (PPA), 40% Glass Fiber Reinforced

Material Notes:

35% Glass Reinforced laser markable PPA High Performance Polyamide Developed for Electrical and Electronics Applications. Zytel HTN54G35EF BK420 is a 35% glass reinforced toughened heat stabilized lubricated high performance polyamide resin developedInformation provided by DuPont Performance Polymers

Order this product through the following link:
http://www.lookpolymers.com/polymer_DuPont-Performance-Polymers-Zytel-HTN-54G35EF-BKB336-Polyphthalamide-PPA-nbspUnverified-Data.php

Physical Properties	Metric	English	Comments
Density	1.38 g/cc	0.0499 lb/in³	DAM; ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	189 MPa	27400 psi	DAM; ISO 527-1/-2
Elongation at Break	2.7 %	2.7 %	DAM; ISO 527-1/-2
Tensile Modulus	11.7 GPa	1700 ksi	DAM; ISO 527-1/-2
Charpy Impact Unnotched	9.00 J/cm²	42.8 ft-lb/in²	DAM; ISO 179/1eU
Charpy Impact, Notched	1.40 J/cm²	6.66 ft-lb/in²	DAM; ISO 179/1eA

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	260 °C	500 °F	DAM; ISO 75-1/-2

Descriptive Properties	Value	Comments
Part Marking Code	>PA-IGF35<	ISO 11469
	>PPA-IGF35<	SAE J1344
Processing	Injection Moulding	
Regional Availability	Asia Pacific	
	Europe	
	Global	
	Near East/Africa	
	North America	

Descriptive Properties	Value	Comments
	South and Central America	
Special Characteristics	Heat stabilised or stable to heat	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China