

DuPont™ Surlyn® 2601B Sodium Ionomer

Category : Polymer , Thermoplastic , Ionomer , Ionomer, Film Grade

Material Notes:

Surlyn® 2601B is available for use in conventional blown, cast film, and sheet extrusion equipment. It is also used in coextrusion equipment designed to process polyethylene and ethylene copolymer type resins. SURLYN® 2601B complies with Food and Drug Administration Regulation 21 CFR 177.1330(a) - - Ionomeric resins, subject to the limitations and requirements therein. This Regulation describes polymers that may be used in contact with food, subject to the finished food-contact article meeting the extractive limitations under the intended conditions of use, as shown in paragraph (c) of the Regulation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DuPont-Surlyn-2601B-Sodium-Ionomer.php

Physical Properties	Metric	English	Comments
Density	0.940 g/cc	0.0340 lb/in³	ASTM D792, ISO 3146
Melt Flow	1.3 g/10 min	1.3 g/10 min	ASTM D1238, ISO 1133
	@Load 2.16 kg, Temperature 190 °C	@Load 4.76 lb, Temperature 374 °F	

Thermal Properties	Metric	English	Comments
Melting Point	60.0 °C	140 °F	Freezing Point; ASTM D3417, ISO 3146
	97.0 °C	207 °F	ASTM D3417, ISO 3146
Vicat Softening Point	71.0 °C	160 °F	ASTM D1525, ISO 306

Processing Properties	Metric	English	Comments
Processing Temperature	<= 285 °C	<= 545 °F	
Feed Temperature	135 °C	275 °F	Blown Film Coextrusion
	160 °C	320 °F	Cast Film/Sheet Processing
Zone 2	160 °C	320 °F	Blown Film Coextrusion
	210 °C	410 °F	Cast Film/Sheet Processing
Zone 3	185 °C	365 °F	Blown Film Coextrusion
	235 °C	455 °F	Cast Film/Sheet Processing
Zone 4	185 °C	365 °F	Blown Film Coextrusion
	235 °C	455 °F	Cast Film/Sheet Processing
Zone 5	185 °C	365 °F	Blown Film Coextrusion

Processing Properties	Metric 235 °C	English 455 °F	Comments Cast Film/Sheet Processing
Adapter Temperature	185 °C	365 °F	Blown Film Coextrusion
	235 °C	455 °F	Cast Film/Sheet Processing
Die Temperature	185 °C	365 °F	Blown Film Coextrusion
	235 °C	455 °F	Cast Film/Sheet Processing
Melt Temperature	160 - 260 °C	320 - 500 °F	Blown/Cast Film Processing

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China