

## DuPont Teijin Films Melinex® 331 Polyester Film, 300 Gauge

Category : Polymer , Film , Thermoplastic , Polyester, TP , Polyester Film

### Material Notes:

Melinex® 331 is an opaque, pearlescent, white film with excellent handling properties that is pretreated on one side to promote adhesion to most industrial coatings. Approvals: UL Recognition - Product has been registered with Underwriters Laboratories. Information provided by DuPont.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_DuPont-Teijin-Films-Melinex-331-Polyester-Film-300-Gauge.php](http://www.lookpolymers.com/polymer_DuPont-Teijin-Films-Melinex-331-Polyester-Film-300-Gauge.php)

Physical Properties	Metric	English	Comments
Density	1.43 g/cc	0.0517 lb/in <sup>3</sup>	ASTM D1505

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	86.2 MPa	12500 psi	ASTM D882A
Film Tensile Strength at Yield, TD	86.2 MPa	12500 psi	ASTM D882A
Film Elongation at Break, MD	135 %	135 %	ASTM D882A
Film Elongation at Break, TD	95 %	95 %	ASTM D882A
Coefficient of Friction, Dynamic	0.30 - 0.40	0.30 - 0.40	A-B; ASTM D1894
Coefficient of Friction, Static	0.30 - 0.40	0.30 - 0.40	ASTM D1894
Film Tensile Strength at Break, MD	159 MPa	23000 psi	ASTM D882A
Film Tensile Strength at Break, TD	186 MPa	27000 psi	ASTM D882A

Thermal Properties	Metric	English	Comments
Shrinkage, MD	1.5 % @Temperature 190 °C, Time 300 sec	1.5 % @Temperature 374 °F, Time 0.0833 hour	Unrestrained
Shrinkage, TD	1.5 % @Temperature 190 °C, Time 300 sec	1.5 % @Temperature 374 °F, Time 0.0833 hour	Unrestrained

Optical Properties	Metric	English	Comments
Gloss	40 %	40 %	45°; ASTM D1003
	45 %	45 %	60°; ASTM D1003
Transmission, Visible	9.3 %	9.3 %	TLT; ASTM D1003

Optical Properties	Metric	English	Comments
--------------------	--------	---------	----------

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)  
Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)  
Tel : +86 021-51131842  
Mobile : +86 13061808058  
Skype : lookpolymers  
Address : United North Road 215,Fengxian District, Shanghai City,China