

DuPont Teijin Films Melinex® S Polyester Film, 200 Gauge

Category : Polymer , Film , Thermoplastic , Polyester, TP , Polyester Film

Material Notes:

Melinex® S is a general purpose film which combines excellent handling characteristics with a slightly hazy appearance. It is available in specific thicknesses from 48 - 500 gauge, and is used for the full range of Melinex® applications. Approvals: UL 94 VTM-2 - for 92 - 500 gauge (0.023 - 0.13mm) and UL Recognition - Product has been registered with Underwriters Laboratories. Information provided by DuPont.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DuPont-Teijin-Films-Melinex-S-Polyester-Film-200-Gauge.php

Physical Properties	Metric	English	Comments
Density	1.40 g/cc	0.0506 lb/in ³	

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	100 MPa	14500 psi	ASTM D882A
Film Tensile Strength at Yield, TD	99.3 MPa	14400 psi	ASTM D882A
Film Elongation at Break, MD	160 %	160 %	ASTM D882A
Film Elongation at Break, TD	100 %	100 %	ASTM D882A
Coefficient of Friction, Dynamic	0.40	0.40	A-B; ASTM D1894
Film Tensile Strength at Break, MD	200 MPa	29000 psi	ASTM D882A
Film Tensile Strength at Break, TD	255 MPa	37000 psi	ASTM D882A

Thermal Properties	Metric	English	Comments
Shrinkage, MD	2.5 % @Temperature 190 °C, Time 300 sec	2.5 % @Temperature 374 °F, Time 0.0833 hour	Unrestrained
Shrinkage, TD	0.50 % @Temperature 190 °C, Time 300 sec	0.50 % @Temperature 374 °F, Time 0.0833 hour	Unrestrained

Optical Properties	Metric	English	Comments
Haze	9.0 %	9.0 %	ASTM D1003
Transmission, Visible	85.5 %	85.5 %	TLT; ASTM D1003

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Electrical Properties	1.00e+17 ohm-cm	1.00e+17 ohm-cm	Comments
Volume Resistivity	Metric	English	100 V DC; ASTM D257
	@Temperature 25.0 °C, Time 100 sec	@Temperature 77.0 °F, Time 0.0278 hour	
Surface Resistivity per Square	1.00e+15 ohm	1.00e+15 ohm	500 V DC @ 50% RH; ASTM D257
	@Temperature 25.0 °C	@Temperature 77.0 °F	
Dielectric Strength	197 kV/mm	5000 kV/in	0.25 inch electrodes in dry air @25°C; ASTM D149-81
Dielectric Breakdown	10000 V	10000 V	0.25 inch electrodes in dry air @25°C; ASTM D149-81

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China