

## DuPont Teijin Films Mylar® M30 Polyester Film, 100 Gauge (25 µm), PVDC Coated (discontinued \*\*)

Category : Polymer , Film , Thermoplastic , Polyester, TP , PVDC , Polyvinyl Dichloride (PVDC) Coated Polyester Film

### Material Notes:

Data provided by DuPont Packaging Polymers. A transparent polyester packaging film, solvent coated on both sides with a PVDC copolymer. The coating is heat sealable, and is an excellent moisture and oxygen barrier. Available in 50, 75, and 100 gauges. Used both in unsupported form, or as a component of a lamination, and can be run on both form-fill-seal and overwrap equipment. It is particularly well suited for the packaging of long shelf life or moisture-and oxygen-sensitive products.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_DuPont-Teijin-Films-Mylar-M30-Polyester-Film-100-Gauge-25-m-PVDC-Coated-nbspdiscontinued.php](http://www.lookpolymers.com/polymer_DuPont-Teijin-Films-Mylar-M30-Polyester-Film-100-Gauge-25-m-PVDC-Coated-nbspdiscontinued.php)

Physical Properties	Metric	English	Comments
Density	1.40 g/cc	0.0506 lb/in <sup>3</sup>	Average value for Mylar® films.
Moisture Vapor Transmission	0.200 cc-mm/m <sup>2</sup> -24hr-atm	0.508 cc-mil/100 in <sup>2</sup> -24hr-atm	ASTM E96 Procedure E
Water Vapor Transmission	8.00 g/m <sup>2</sup> /day	0.515 g/100 in <sup>2</sup> /day	ASTM E96 Procedure E
Oxygen Transmission	0.200 cc-mm/m <sup>2</sup> -24hr-atm	0.508 cc-mil/100 in <sup>2</sup> -24hr-atm	or 8 cc/m <sup>2</sup> -24hr-atm for the film. ASTM D3985

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	130 %	130 %	ASTM D882
Film Elongation at Break, TD	75 %	75 %	ASTM D882
Modulus of Elasticity	3.79 GPa	550 ksi	(stiffness), ASTM D882
Tear Strength Test	500	500	Graves, g; ASTM D1004
Seal Strength	201 g/25 mm	201 g/in	
Film Tensile Strength at Break, MD	179 MPa	26000 psi	ASTM D882
Film Tensile Strength at Break, TD	248 MPa	36000 psi	ASTM D882

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	121 °C	250 °F	Not cleared by FDA for food temperatures above this temperature.
Shrinkage	3.0 % @Temperature 150 °C, Time 1800 sec	3.0 % @Temperature 302 °F, Time 0.500 hour	Film shrinkage in oven.

Optical Properties	Metric	English	Comments
Haze	2.5 %	2.5 %	ASTM D1003
Gloss	180 %	180 %	20°; ASTM D2457
Transmission, Visible	90 %	90 %	transparent; thickness not quantified

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China