## DuPont Teijin Films Mylar® S1 Polyester Film, 20 Gauge

Category : Polymer , Film , Thermoplastic , Polyester, TP , Polyester Film

## Material Notes:

Mylar® S1 films are slightly hazy with surfaces tailored to provide excellent handling and product functionality for a variety of industrial end uses. The outstanding tensile properties and thermal stability typical of Mylar® S1 films are maintained through all gauges offered.General Product Info: Mylar® S1 films have balanced tensile properties with a service range of -94 to 302°F. They are extremely resistant to most chemicals and aging embrittlement.Typical Applications: Decorative metalizingTape substratesFlexible ductingBook jacket laminationsRelease sheetPhoto substratesPressure-sensitive tapeThermal reflectorsProtective surfacingCarbon-coated ribbonPhoto resistStationery suppliesMicroformsInformation provided by DuPont.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_DuPont-Teijin-Films-Mylar-S1-Polyester-Film-20-Gauge.php

Physical Properties	Metric	English	Comments
Density	1.39 g/cc	0.0502 lb/in <sup>3</sup>	Typical Mylar®; ASTM D1505
Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	110 %	110 %	ASTM D882A
Film Tensile Strength at Break, MD	179 MPa	26000 psi	ASTM D882A

Thermal Properties	Metric	English	Comments	
Specific Heat Capacity	1.17 J/g-°C	0.280 BTU/lb-°F	Typical Mylar®	
Melting Point	254 °C	489 °F	Typical Mylar® via DSC	
Maximum Service Temperature, Air	150 °C	302 °F		
Maximum Service Temperature, Inert	-70.0 °C	-94.0 °F		
Shrinkage, MD	2.1 %	2.1 %	Unrestrained	
	@Temperature 150 °C, Time 1800 sec	@Temperature 302 °F, Time 0.500 hour		
Shrinkage, TD	1.1 %	1.1 %		
	@Temperature 150 °C, Time 1800 sec	@Temperature 302 °F, Time 0.500 hour	Unrestrained	

Optical Properties	Metric	English	Comments
Haze	4.5 %	4.5 %	ASTM D1003

	Descriptive Properties	Value	Comments
--	------------------------	-------	----------

**Descriptive Properties** 

Value

Comments

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China