## DuPont Teijin Films Teijin® Tetoron® OX Polyester Film, 200 Gauge

Category : Polymer , Film , Thermoplastic , Polyester, TP , Polyester Film

## Material Notes:

Teijin® Tetoron® O is the designation for a family of super clear polyester films. They have very smooth surface characteristics and are knurled. The combination of smoothness and knurling provide wrinkle-free roll formation. The following Teijin® Tetoron® O film variants are available: O: Non-pretreated, knurledOX: Slip Pretreated (one side)OFW: Adhesion Pretreated (two side)OLY: Adhesion Pretreated (one side), low shrinkageOLW: Pretreated (two side), low shrinkageTypical Applications: LabelsDecorative LaminatesSolar Control FilmImagingReflection FilmMetallizationInformation provided by DuPont.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_DuPont-Teijin-Films-Teijin-Tetoron-OX-Polyester-Film-200-Gauge.php

| Mechanical Properties              | Metric    | English   | Comments   |
|------------------------------------|-----------|-----------|------------|
| Film Elongation at Break, MD       | 140 %     | 140 %     | ASTM D882A |
| Film Elongation at Break, TD       | 120 %     | 120 %     | ASTM D882A |
| Coefficient of Friction, Dynamic   | 0.36      | 0.36      | ASTM D1894 |
| Coefficient of Friction, Static    | 0.38      | 0.38      | ASTM D1894 |
| Film Tensile Strength at Break, MD | 283.9 MPa | 41180 psi | ASTM D882A |
| Film Tensile Strength at Break, TD | 293.9 MPa | 42630 psi | ASTM D882A |

| Thermal Properties | Metric                                | English                                 | Comments     |
|--------------------|---------------------------------------|---|--------------|
| Shrinkage, MD      | 1.8 %                                 | 1.8 %                                   | Unrestrained |
|                    | @Temperature 150 °C,<br>Time 1800 sec | @Temperature 302 °F,<br>Time 0.500 hour |              |
| Shrinkage, TD      | 0.20 %                                | 0.20 %                                  | Unrestrained |
|                    | @Temperature 150 °C,<br>Time 1800 sec | @Temperature 302 °F,<br>Time 0.500 hour |              |

| Optical Properties | Metric | English | Comments   |
|--------------------|--------|---------|------------|
| Haze               | 0.50 % | 0.50 %  | ASTM D1003 |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058



Skype : lookpolymers Address : United North Road 215, Fengxian District, Shanghai City, China