

DuPont Vamac® GLS Sample Compound

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Compounds of Vamac® are formulated and processed by customers to meet their own specific performance requirements. Many of the highest-performing compounds and vulcanizates of Vamac® GLS are thus proprietary, and cannot be published by DuPont. DuPont has independently formulated a wide variety of Vamac® compounds for its own short- and long-term properties testing programs. A typical compound of Vamac® GLS is reviewed below. Information provided by DuPont.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DuPont-Vamac-GLS-Sample-Compound.php

Physical Properties	Metric	English	Comments
Mooney Viscosity	>= 14.9	>= 14.9	Mooney Units

Descriptive Properties	Value	Comments
Armeen® 18D	0.5 parts	
Diak No. 1	1.5 parts	
DOTG Coaccelerator	4 parts	
FEF Black(N550)	60 parts	
Naugard® 445 antioxidant	2 parts	
Stearic Acid	1.5 parts	
Time for 10 unit Mooney Viscosity Rise	10.1 minutes	
TP-759	10 parts	
Vamac® GLS	100 parts	
Vanfre® VAM	1 part	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China