

E-Polymers TEKAMID® TA210GR , 33% Glass Fiber Reinforced PA66, DAM

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled

Material Notes:

33% Glass Fiber reinforced, Anti EG, Anti Hydrolysis Information provided by E-Polymers Co. Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_E-Polymers-TEKAMID-TA210GR-33-Glass-Fiber-Reinforced-PA66-DAM.php

Physical Properties	Metric	English	Comments
Density	1.37 g/cc	0.0495 lb/in ³	ASTM D792
Water Absorption	0.70 %	0.70 %	23°C/24 hr; ASTM D570
Linear Mold Shrinkage	0.0040 cm/cm	0.0040 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	160 MPa	23200 psi	ASTM D638
Elongation at Break	2.0 %	2.0 %	ASTM D638
Flexural Yield Strength	270 MPa	39200 psi	ASTM D790
Flexural Modulus	7.50 GPa	1090 ksi	ASTM D790
Izod Impact, Notched	0.900 J/cm	1.69 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	ASTM D2133
Deflection Temperature at 0.46 MPa (66 psi)	260 °C	500 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	252 °C	486 °F	ASTM D648
Flammability, UL94	HB	HB	

Processing Properties	Metric	English	Comments
Mold Temperature	80.0 - 100 °C	176 - 212 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China