

E-Polymers TEKAPPO® J930 30% Glass Fiber Reinforced M-PPO

Category : Polymer , Thermoplastic , Polyphenylene Ether/PPO , Polyphenylene Ether, 30% Glass Filled

Material Notes:

Modified PPO/PPE: TEKAPPO is a modified PPO/PPE, blending PPO with HIPS in order to improve HDT and processability. It displays various HDT range with halogen-free flammability, impact resistance and reinforced fiberglass. It shows high dimensional stability and rigidity used for housing and electrical parts. Information Provided by E-Polymers Co., Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_E-Polymers-TEKAPPO-J930-30-Glass-Fiber-Reinforced-M-PPO.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.29 g/cc	1.29 g/cc	ASTM D792
Water Absorption	0.060 % @Time 86400 sec	0.060 % @Time 24.0 hour	
Linear Mold Shrinkage	0.0010 cm/cm	0.0010 in/in	
Linear Mold Shrinkage, Transverse	0.0040 cm/cm	0.0040 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength	98.1 MPa	14200 psi	ASTM D638
Elongation at Break	5.0 %	5.0 %	ASTM D638
Flexural Strength	156.96 MPa	22765 psi	ASTM D790
Flexural Modulus	6.867 GPa	996.0 ksi	ASTM D790
Izod Impact, Notched	1.08 J/cm	2.02 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	158 °C	316 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	138 °C	280 °F	ASTM D648
Flammability, UL94	HB	HB	

Processing Properties	Metric	English	Comments
Melt Temperature	280 - 310 °C	536 - 590 °F	
Mold Temperature	80.0 - 100 °C	176 - 212 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China