

EMS-Grivory Grivory® G 21 PA6I/6T

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

Product description: Grivory G 21 natural 6506 is a high viscosity, partially aromatic, amorphous copolyamide with processing aid. Improved gas and aroma barrier at elevated relative humidityExcellent flavor and aroma barrierGood Barrier against UV-radiationHighly transparentHigh surface glossGood chemical resistanceVery good abrasion resistance Application examples: Grivory G 21 natural 6506 is suitable as well for the manufacture of coextruded blown film, mono or coex cast film and coextruded tubes as the production of mono and multilayer containers. Grivory G 21 natural 6506 is also used as an additive for polyamide 6 and different copolyamides to improve film properties. Barrier layer for mono- or co-extruded rigid packaging (EBM or ISBM bottles).Information provided by EMS Grivory

Order this product through the following link:

http://www.lookpolymers.com/polymer_EMS-Grivory-Grivory-G-21-PA6I6T.php

Physical Properties	Metric	English	Comments
Density	1.18 g/cc	0.0426 lb/in ³	ISO 1183
Water Absorption	7.0 %	7.0 %	ISO 62
Moisture Absorption	2.00 %	2.00 %	ISO 62
Water Vapor Transmission	7.00 g/m ² /day	0.451 g/100 in ² /day	23°C/85%r.h.; DIS 15106-1/-2
Oxygen Transmission Rate	10.0 cc/m ² /day	0.644 cc/100 in ² /day	23°C/85%r.h.; DIS 15105-1/-2
	30.0 cc/m ² /day	1.93 cc/100 in ² /day	23°C/0%r.h.; DIS 15105-1/-2
Carbon Dioxide Transmission	40.0 cc-mm/m ² -24hr-atm	102 cc-mil/100 in ² -24hr-atm	23°C/85%r.h.; DIS 15105-1/-2
	90.0 cc-mm/m ² -24hr-atm	229 cc-mil/100 in ² -24hr-atm	23°C/0%r.h.; DIS 15105-1/-2
Melt Flow	25 g/10 min	25 g/10 min	(MVR) [cm ³ /10min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	85.0 MPa	12300 psi	ISO 527-3
Film Tensile Strength at Yield, TD	85.0 MPa	12300 psi	ISO 527-3
Film Elongation at Break, MD	300 %	300 %	ISO 527-3
Film Elongation at Break, TD	300 %	300 %	ISO 527-3
Film Elongation at Yield, MD	5.0 %	5.0 %	ISO 527-3
Film Elongation at Yield, TD	5.0 %	5.0 %	ISO 527-3
Tensile Modulus	3.00 GPa	435 ksi	conditioned; ISO 527-1/-2

Mechanical Properties	MetricPa	English	Comments7-1/-2
Charpy Impact, Notched	0.800 J/cm²	3.81 ft-lb/in²	dry; ISO 179/1eA
	0.800 J/cm²	3.81 ft-lb/in²	conditioned; ISO 179/1eA
	0.200 J/cm²	0.952 ft-lb/in²	conditioned; ISO 179/1eU
	@Temperature 30.0 °C	@Temperature 86.0 °F	
	0.800 J/cm²	3.81 ft-lb/in²	dry; ISO 179/1eU
	@Temperature 30.0 °C	@Temperature 86.0 °F	
Tear Strength	5.00 kN/m	28.5 pli	Trouser Tear resistance MD; ISO 6383-1
	5.00 kN/m	28.5 pli	Trouser Tear resistance TD; ISO 6383-1
Elmendorf Tear Strength MD	1020 g	1020 g	ISO 6383-2
Elmendorf Tear Strength TD	1020 g	1020 g	ISO 6383-2
Film Tensile Strength at Break, MD	85.0 MPa	12300 psi	ISO 527-3
Film Tensile Strength at Break, TD	85.0 MPa	12300 psi	ISO 527-3

Thermal Properties	Metric	English	Comments
Transformation Temperature, Tg	125 °C	257 °F	10°C/min; ISO 11357-1/-2

Optical Properties	Metric	English	Comments
Gloss	160 %	160 %	60°; ISO 2813
Transmission, Visible	90 %	90 %	transparent; thickness not quantified

Descriptive Properties	Value	Comments
Food contact	EU Requirements	
	FDA	
Form	Granules	
Medical	USP VI	
Packaging	Blow moulded containers	
	Cosmetics / Personal care	
	Injectionstretchblowmoulded containers	

Descriptive Properties	Non oriented film Value	Comments
	Oriented film	
	Paper coating	
	Tubes	
Processing	Blown Film Extrusion	
	Extrusion - blow molding	
	Film Extrusion	
	Injection Molding	
	Other Extrusion	
Product Attributes	Barrier Properties	
	Partially aromatic Polyamide	
Special Characteristics	Transparent	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China