

EMS-Grivory Grivory® L 20 W 20 PA12

Category : Polymer , Thermoplastic , Nylon , Nylon 12

Material Notes:

Product Description: Grilamid L 20 W 20 is a semi-flexible plasticized medium viscosity polyamide 12 (PA12) extrusion grade. Grilamid L 20 W 20 is heat stabilized. The main features of Grilamid L 20 W 20 are: Heat stability Good impact strength Good chemical resistance Low weight, low density FlexibleApplication examples: Grilamid L 20 W 20 has been developed for tube extrusion applications in automotive and industrial market segments.Information provided by EMS Grivory

Order this product through the following link:

http://www.lookpolymers.com/polymer_EMS-Grivory-Grivory-L-20-W-20-PA12.php

Physical Properties	Metric	English	Comments
Density	1.03 g/cc	0.0372 lb/in ³	ISO 1183
Water Absorption	1.5 %	1.5 %	ISO 62
Moisture Absorption	0.700 %	0.700 %	ISO 62
Linear Mold Shrinkage, Flow	0.0080 cm/cm	0.0080 in/in	ISO 294-4, 2577
Linear Mold Shrinkage, Transverse	0.010 cm/cm	0.010 in/in	ISO 294-4, 2577

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	64	64	conditioned, 15s; ISO 868
Tensile Strength at Break	60.0 MPa	8700 psi	dry; ISO 527-1/-2
	60.0 MPa	8700 psi	conditioned; ISO 527-1/-2
Tensile Strength, Yield	30.0 MPa	4350 psi	dry; ISO 527-1/-2
	30.0 MPa	4350 psi	dry; ISO 527-1/-2
Elongation at Break	>= 50 %	>= 50 %	conditioned; ISO 527-1/-2
	<= 50 %	<= 50 %	dry; ISO 527-1/-2
Elongation at Yield	20 %	20 %	conditioned; ISO 527-1/-2
	20 %	20 %	dry; ISO 527-1/-2
Tensile Modulus	0.500 GPa	72.5 ksi	conditioned; ISO 527-1/-2
	0.650 GPa	94.3 ksi	dry; ISO 527-1/-2
Charpy Impact Unnotched	NB	NB	dry; ISO 179/1eU
	NB	NB	conditioned; ISO 179/1eU

Mechanical Properties	NB Metric	NB English	Comments dry, ISO 179/1eU
	@Temperature 30.0 °C	@Temperature 86.0 °F	
	NB	NB	conditioned; ISO 179/1eU
	@Temperature 30.0 °C	@Temperature 86.0 °F	
Charpy Impact, Notched	4.00 J/cm²	19.0 ft-lb/in²	conditioned; ISO 179/1eA
	0.300 J/cm²	1.43 ft-lb/in²	conditioned; ISO 179/1eU
	@Temperature 30.0 °C	@Temperature 86.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	140 µm/m-°C	77.8 µin/in-°F	ISO 11359-1/-2
CTE, linear, Transverse to Flow	160 µm/m-°C	88.9 µin/in-°F	ISO 11359-1/-2
Melting Point	174 °C	345 °F	10°C/min; ISO 11357-1/-3
Maximum Service Temperature, Air	80.0 - 100 °C	176 - 212 °F	long term; EMS
	150 °C	302 °F	short term; EMS
Deflection Temperature at 0.46 MPa (66 psi)	100 °C	212 °F	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	45.0 °C	113 °F	ISO 75-1/-2
Flammability, UL94	HB	HB	IEC 60695-11-10

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+13 ohm-cm	1.00e+13 ohm-cm	conditioned; IEC 60093
Surface Resistance	1.00e+12 ohm	1.00e+12 ohm	IEC 60093
Dielectric Strength	32.0 kV/mm	813 kV/in	conditioned; IEC 60243-1
Comparative Tracking Index	600 V	600 V	conditioned; IEC 60112

Descriptive Properties	Value	Comments
Additives	Plasticizer	
Automotive	Compressed air systems	
	Powertrain and Chassis	
Electricals & Electronics	Cables & Tubes	
Form	Granules	

Descriptive Properties	Value	Comments
	Mechanical Engineering	
Processing	Other Extrusion	
Product Attributes	Flexible	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China