

Eastman Eastar DN101 PCTG Copolyester (discontinued **)

Category : Polymer , Thermoplastic , Polyester, TP , Polycyclohexylenedimethylene Terephthalate (PCT) , Glycol-Modified PCT (PCTG) Copolyester

Material Notes:

ISO data as provided by the manufacturer, Eastman Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eastman-Eastar-DN101-PCTG-Copolyester-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in ³	
Linear Mold Shrinkage, Flow	0.0020 - 0.0050 cm/cm	0.0020 - 0.0050 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	42.0 MPa	6090 psi	50 mm/min
Elongation at Break	>= 50 %	>= 50 %	
Elongation at Yield	4.2 %	4.2 %	
Tensile Modulus	1.40 GPa	203 ksi	1mm/min
Charpy Impact Unnotched	NB	NB	
	NB	NB	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	2.50 J/cm ²	11.9 ft-lb/in ²	
	0.640 J/cm ²	3.05 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	82.0 µm/m-°C	45.6 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
CTE, linear, Transverse to Flow	61.0 µm/m-°C	33.9 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Melting Point	222 °C	432 °F	
Deflection Temperature at 0.46 MPa (66 psi)	73.0 °C	163 °F	
Deflection Temperature at 1.8 MPa (264 psi)	66.0 °C	151 °F	

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	82.0 °C	180 °F	

Processing Properties	Metric	English	Comments
Melt Temperature	275 - 295 °C	527 - 563 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China