

Eastman Tenite 105-28 Cellulose Acetate (discontinued **)

Category : Polymer , Renewable/Recycled Polymer , Thermoplastic , Cellulosic , Cellulose Acetate, Molded

Material Notes:

28% Plasticized ISO data as provided by the manufacturer, Eastman Chemical.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eastman-Tenite-105-28-Cellulose-Acetate-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.27 g/cc	0.0459 lb/in ³	
Linear Mold Shrinkage, Flow	0.0020 - 0.0060 cm/cm	0.0020 - 0.0060 in/in	
	@Thickness 3.20 mm	@Thickness 0.126 in	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	34.0 MPa	4930 psi	50 mm/min
Elongation at Break	19 %	19 %	
Elongation at Yield	3.5 %	3.5 %	
Tensile Modulus	2.01 GPa	292 ksi	1mm/min
Charpy Impact Unnotched	NB	NB	
	NB	NB	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	1.59 J/cm ²	7.57 ft-lb/in ²	
	0.470 J/cm ²	2.24 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	84.0 µm/m-°C	46.7 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
CTE, linear, Transverse to Flow	145 µm/m-°C	80.6 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	88.0 °C	190 °F	
Deflection Temperature at 1.8 MPa (264 psi)	82.0 °C	180 °F	

Vicat Softening Point Thermal Properties	85.0 °C Metric	185 °F English	Comments
Glass Transition Temp, Tg	95.0 °C	203 °F	

Processing Properties	Metric	English	Comments
Melt Temperature	220 - 240 °C	428 - 464 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China