

Eastman Tenite 358-15 CAP Cellulose Acetate Propionate (discontinued **)

Category : Polymer , Renewable/Recycled Polymer , Thermoplastic , Cellulosic , Cellulose Acetate Propionate, Molded

Material Notes:

15% Plasticized. ISO data as provided by the manufacturer, Eastman Chemical.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eastman-Tenite-358-15-CAP-Cellulose-Acetate-Propionate-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in ³	
Linear Mold Shrinkage, Flow	0.0020 - 0.0060 cm/cm	0.0020 - 0.0060 in/in	
	@Thickness 3.20 mm	@Thickness 0.126 in	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	28.0 MPa	4060 psi	50 mm/min
Elongation at Break	34 %	34 %	
Elongation at Yield	3.7 %	3.7 %	
Tensile Modulus	1.41 GPa	205 ksi	1mm/min
Charpy Impact Unnotched	NB	NB	
	NB	NB	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	2.61 J/cm ²	12.4 ft-lb/in ²	
	0.720 J/cm ²	3.43 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	112 µm/m-°C	62.2 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
CTE, linear, Transverse to Flow	133 µm/m-°C	73.9 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	86.0 °C	187 °F	
Deflection Temperature at 1.8 MPa (264 psi)	77.0 °C	171 °F	

Vicat Softening Point Thermal Properties	81.0 °C Metric	178 °F English	Comments
Glass Transition Temp, Tg	90.0 °C	194 °F	

Processing Properties	Metric	English	Comments
Melt Temperature	210 - 220 °C	410 - 428 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China