

Eastman Tenite 383A-08 Cellulose Acetate Propionate (discontinued **)

Category : Polymer , Renewable/Recycled Polymer , Thermoplastic , Cellulosic , Cellulose Acetate Propionate, Molded

Material Notes:

8% Plasticized. ISO data as provided by the manufacturer, Eastman Chemical.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eastman-Tenite-383A-08-Cellulose-Acetate-Propionate-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	
Linear Mold Shrinkage, Flow	0.0020 - 0.0060 cm/cm	0.0020 - 0.0060 in/in	
	@Thickness 3.20 mm	@Thickness 0.126 in	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	37.0 MPa	5370 psi	50 mm/min
Elongation at Break	>= 50 %	>= 50 %	
Elongation at Yield	4.0 %	4.0 %	
Tensile Modulus	1.74 GPa	252 ksi	1mm/min
Charpy Impact Unnotched	NB	NB	
	NB	NB	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	1.42 J/cm ²	6.76 ft-lb/in ²	
	0.440 J/cm ²	2.09 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	99.0 µm/m-°C	55.0 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
CTE, linear, Transverse to Flow	134 µm/m-°C	74.4 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	95.0 °C	203 °F	
Deflection Temperature at 1.8 MPa (264 psi)	88.0 °C	190 °F	

Vicat Softening Point Thermal Properties	95.0 °C Metric	203 °F English	Comments
Glass Transition Temp, Tg	110 °C	230 °F	

Processing Properties	Metric	English	Comments
Melt Temperature	240 - 250 °C	464 - 482 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China