

Eastman Tritan TX1800 Copolyester

Category : Polymer , Thermoplastic , Polyester, TP

Material Notes:

Applications:Consumer and durable goodsExtrusion blow moldingInjection stretch blow molding**Key Attributes:**Ease of processingExcellent clarityExcellent Hydrolytic stabilityGood chemical resistanceGood heat resistanceOutstanding impact resistance**Product Description:**Eastman Tritan Copolyester TX1800 is an amorphous copolyester specifically developed for use in blow molding applications. Its most outstanding features are excellent toughness, hydrolytic stability, heat resistance, and chemical resistance. In addition, this new generation copolyester offers excellent appearance and clarity. Eastman Tritan Copolyester TX1800 may be used in repeated use food contact articles under United States Food and Drug Administration (FDA) regulations. This product is certified to NSF/ANSI Standard 51 for Food Equipment Materials.Information provided by Eastman.

Order this product through the following link:
http://www.lookpolymers.com/polymer_Eastman-Tritan-TX1800-Copolyester.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.18 g/cc	1.18 g/cc	ASTM D792
Linear Mold Shrinkage	0.0060 cm/cm	0.0060 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	110	110	ASTM D785
Tensile Strength at Break	52.0 MPa	7540 psi	ASTM D638
Tensile Strength, Yield	45.0 MPa	6530 psi	ASTM D638
Elongation at Break	139 %	139 %	ASTM D638
Elongation at Yield	7.0 %	7.0 %	ASTM D638
Tensile Modulus	1.609 GPa	233.4 ksi	ASTM D638
Flexural Strength	64.0 MPa	9280 psi	ASTM D790
Flexural Modulus	1.522 GPa	220.7 ksi	ASTM D790
Izod Impact, Notched	8.42 J/cm	15.8 ft-lb/in	ASTM D256
Izod Impact, Unnotched	NB	NB	ASTM D4812
Puncture Energy	62.0 J	45.7 ft-lb	at Max load; ASTM D3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	65.0 J	47.9 ft-lb	at Max load; ASTM D3763
	@Temperature 0.000 °C	@Temperature 32.0 °F	

Mechanical Properties	67.0 J Metric	49.4 ft-lb English	Comments
	@Temperature -40.0 °C	@Temperature -40.0 °F	1; ASTM D3763

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	101 °C	214 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	85.0 °C	185 °F	ASTM D648

Optical Properties	Metric	English	Comments
Haze	<= 1.0 %	<= 1.0 %	ASTM D1003
Transmission, Visible	91 %	91 %	Total; ASTM D1003

Processing Properties	Metric	English	Comments
Melt Temperature	235 - 255 °C	455 - 491 °F	EBM
	260 - 280 °C	500 - 536 °F	ISBM
Mold Temperature	15.0 - 50.0 °C	59.0 - 122 °F	EBM
	35.0 - 55.0 °C	95.0 - 131 °F	ISBM Blow Mold
	40.0 - 65.0 °C	104 - 149 °F	ISBM Injection Mold
Drying Temperature	88.0 °C	190 °F	
Dry Time	4 - 6 hour	4 - 6 hour	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China