

Ecomass® 1080ZB92 Filled Polyamide

Category : Polymer , Thermoplastic , Nylon

Material Notes:

Nontoxic alternative to Lead (Pb), radiation shielding applications.Moderate Specific GravityFilled Polyamide (PA) alloyExcellent

ToughnessInformation provided by Technical Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ecomass-1080ZB92-Filled-Polyamide.php

Physical Properties	Metric	English	Comments
Specific Gravity	6.90 g/cc	6.90 g/cc	ASTM D792
Linear Mold Shrinkage	0.0050 - 0.0060 cm/cm	0.0050 - 0.0060 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	34.5 MPa	5000 psi	ASTM D638
Elongation at Break	3.75 %	3.75 %	ASTM D638
Tensile Modulus	6.45 GPa	935 ksi	ASTM D638
Flexural Strength	49.0 MPa	7100 psi	ASTM D790
Flexural Modulus	6.41 GPa	930 ksi	ASTM D790
Izod Impact, Notched	1.44 J/cm	2.70 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	121 °C	250 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	107 °C	225 °F	ASTM D648

Processing Properties	Metric	English	Comments
Melt Temperature	232 - 260 °C	450 - 500 °F	
Mold Temperature	65.6 - 82.2 °C	150 - 180 °F	
Drying Temperature	73.9 °C	165 °F	
Dry Time	4 hour	4 hour	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China