

Ecomass® 3620BX60 18% Borated Polyethylene (HDPE)

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE

Material Notes:

18% Borated Polyethylene (HDPE), Product Form - Pellets, No Pre-Drying Required
Processing Method: Injection Molding, Compression Molding
Neutron Shielding Applications
Information provided by Technical Polymers.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ecomass-3620BX60-18-Borated-Polyethylene-HDPE.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.35 g/cc	1.35 g/cc	ASTM D792
Linear Mold Shrinkage	0.0060 - 0.010 cm/cm	0.0060 - 0.010 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength	10.0 MPa	1450 psi	ASTM D638
Elongation at Break	8.0 %	8.0 %	ASTM D638
Tensile Modulus	2.07 GPa	300 ksi	ASTM D638
Flexural Strength	13.8 MPa	2000 psi	ASTM D790
Flexural Modulus	1.93 GPa	280 ksi	ASTM D790
Izod Impact, Notched	1.07 J/cm	2.00 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	76.7 °C	170 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	65.6 °C	150 °F	ASTM D648

Processing Properties	Metric	English	Comments
Melt Temperature	177 - 227 °C	350 - 440 °F	
Mold Temperature	21.1 - 65.6 °C	70.0 - 150 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China