

Ecomass® 4703ZC76 Stainless Steel Filled Polyurethane

Category : Polymer , Thermoplastic , Polyurethane, TP

Material Notes:

Nontoxic alternative to Lead (Pb), weighting and balancing applications
Moderate Specific Gravity
Stainless Steel Filled Polyurethane (TPU)
Flexible
Information provided by Technical Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ecomass-4703ZC76-Stainless-Steel-Filled-Polyurethane.php

Physical Properties	Metric	English	Comments
Specific Gravity	3.40 g/cc	3.40 g/cc	ASTM D792
Linear Mold Shrinkage	0.0060 - 0.0090 cm/cm	0.0060 - 0.0090 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	18.6 MPa	2700 psi	ASTM D638
Elongation at Break	200 %	200 %	ASTM D638
Tensile Modulus	0.517 GPa	75.0 ksi	ASTM D638
Flexural Strength	41.4 MPa	6000 psi	ASTM D790
Flexural Modulus	0.167 GPa	24.2 ksi	ASTM D790
Izod Impact, Notched	2.67 J/cm	5.00 ft-lb/in	ASTM D256

Processing Properties	Metric	English	Comments
Melt Temperature	204 - 221 °C	400 - 430 °F	
Mold Temperature	10.0 - 26.7 °C	50.0 - 80.0 °F	
Drying Temperature	82.2 °C	180 °F	
Dry Time	2 hour	2 hour	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China