

Elastocon TPE Technologies Elastocon® 8038N Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

Elastocon® 8038N is a colorable thermoplastic elastomer formulated for applications that require rubber-like properties and a good surface finish. Elastocon® 8038N is FDA compliant and well suited for consumer goods and industrial applications requiring U.V. stability.

Elastocon® 8038N can be overmolded to polypropylene. Information provided by Elastocon® TPE Technologies

Order this product through the following link:

http://www.lookpolymers.com/polymer_Elastocon-TPE-Technologies-Elastocon-8038N-Thermoplastic-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.015 - 0.025 cm/cm	0.015 - 0.025 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	40	40	ASTM D2240
Tensile Strength, Yield	3.38 MPa	490 psi	ASTM D412
Elongation at Break	620 %	620 %	ASTM D412
100% Modulus	0.00128 GPa	0.186 ksi	ASTM D412
Compression Set	13 % @Time 79200 sec	13 % @Time 22.0 hour	ASTM D395B

Processing Properties	Metric	English	Comments
Feed Temperature	79.0 °C	174 °F	
Rear Barrel Temperature	143 - 160 °C	290 - 320 °F	
Front Barrel Temperature	160 - 177 °C	320 - 350 °F	
Nozzle Temperature	177 - 199 °C	350 - 390 °F	
Mold Temperature	21.1 - 37.8 °C	70.0 - 100 °F	
Back Pressure	0.345 - 0.689 MPa	50.0 - 100 psi	

Descriptive Properties	Value	Comments
Injection Rate	Fast	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China