

Elastocon TPE Technologies Elastocon® 8058HL Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

Elastocon® 8058HL is a colorable thermoplastic elastomer formulated for applications that require rubber-like properties and a reduced coefficient of friction. Elastocon® 8058HL is FDA compliant and well suited for consumer goods and industrial applications requiring U.V. stability. Elastocon® 8058HL can be overmolded to polypropylene. Information provided by Elastocon TPE Technologies, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Elastocon-TPE-Technologies-Elastocon-8058HL-Thermoplastic-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.03 g/cc	1.03 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.012 - 0.022 cm/cm	0.012 - 0.022 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	58	58	ASTM D2240
Tensile Strength	5.67 MPa	822 psi	ASTM D412
Elongation at Break	689 %	689 %	ASTM D412
100% Modulus	0.00198 GPa	0.287 ksi	ASTM D412
Compression Set	17 % @Temperature 20.0 °C, Time 79200 sec	17 % @Temperature 68.0 °F, Time 22.0 hour	ASTM D395B

Processing Properties	Metric	English	Comments
Feed Temperature	<= 79.4 °C	<= 175 °F	
Rear Barrel Temperature	174 - 191 °C	345 - 375 °F	
Front Barrel Temperature	179 - 196 °C	355 - 385 °F	
Nozzle Temperature	185 - 204 °C	365 - 400 °F	
Mold Temperature	21.1 - 37.8 °C	70.0 - 100 °F	
Back Pressure	0.345 - 0.689 MPa	50.0 - 100 psi	

Descriptive Properties	Value	Comments
Injection Rate	Moderate to Fast	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China