

Elektro-Isola Etronit IS Phenolic, Paper Reinforcement, Dark Brown, Sheets

Category : Polymer , Thermoset , Phenolic

Material Notes:

Description: Very good high-voltage insulation material. Very high breakdown voltage, in particular parallel to the layers. Dimensionally stable. Application: Insulation material in high-voltage tap changers. Information provided by Elektro-Isola

Order this product through the following link:

http://www.lookpolymers.com/polymer_Elektro-Isola-Etronit-IS-Phenolic-Paper-Reinforcement-Dark-Brown-Sheets.php

Physical Properties	Metric	English	Comments
Density	1.35 g/cc	0.0488 lb/in ³	24hr/23°C/50% RH; ISO 1183-A; IEC/EN 60893-2 8.1
Water Absorption	1.33 %	1.33 %	24hr/50°C+24hr in water at 23°C, Test Specimen 50x50x3[mm]; ISO 62-1; IEC/EN 60893-2 8.2

Mechanical Properties	Metric	English	Comments
Tensile Strength	110 MPa @Thickness >=1.50 mm	16000 psi @Thickness >=0.0591 in	24hr/23°C/50% RH; ISO 527; IEC/EN 60893-2 5.6
Modulus of Elasticity	8.00 GPa @Thickness >=1.50 mm	1160 ksi @Thickness >=0.0591 in	24hr/23°C/50% RH; ISO 178; IEC/EN 60893-2 5.2
Flexural Strength	140 MPa @Thickness >=1.50 mm	20300 psi @Thickness >=0.0591 in	24hr/23°C/50% RH; ISO 178; IEC/EN 60893-2 5.1
Compressive Strength	300 MPa @Thickness >=5.00 mm	43500 psi @Thickness >=0.197 in	24hr/23°C/50% RH; ISO 604; IEC/EN 60893-2 5.3
Shear Strength	35.0 MPa @Thickness >=5.00 mm	5080 psi @Thickness >=0.197 in	24hr/23°C/50% RH; IEC/EN 60893-2 5.5
Izod Impact, Notched (ISO)	3.50 kJ/m ² @Thickness >=5.00 mm	1.67 ft-lb/in ² @Thickness >=0.197 in	24hr/23°C/50% RH; ISO 180/2A; IEC/EN 60893-2 5.4.3

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Inert	120 °C @Thickness 0.000 mm, Time 7.20e+7 sec	248 °F @Thickness 0.000 in, Time 20000 hour	IEC 60216; IEC/EN 60893-2 7.1

Electrical Properties	Metric	English	Comments
Insulation Resistance	1.00e+8 ohm	1.00e+8 ohm	24hr/50°C+24h in water at 23°C; IEC 60167; IEC/EN 60893-2 6.3
	@Thickness >=3.00 mm	@Thickness >=0.118 in	
Dielectric Constant	5.0	5.0	96hr/105°C+1hr/23°C/20%RH; IEC 60250; IEC/EN 60893-2 6.2
	@Thickness <=3.00 mm, Frequency 50.0 Hz	@Thickness <=0.118 in, Frequency 50.0 Hz	
Dielectric Strength	3.20 kV/mm	81.3 kV/in	96hr/105°C/+1hr/oil 90°C; Parallel; IEC 60245-1; IEC/EN 60893-2 6.1.3.2
	@Thickness >=3.00 mm	@Thickness >=0.118 in	
	14.0 kV/mm	356 kV/in	24hr/23°C/50% RH+1hr/oil 90°C; Perpendicular; IEC 60245-1; IEC/EN 60893-2 6.1.3.1
	@Thickness 3.00 mm	@Thickness 0.118 in	
Dissipation Factor	0.020	0.020	96hr/105°C+1hr/23°C/20%RH; IEC 60250; IEC/EN 60893-2 6.2
	@Frequency 50.0 Hz	@Frequency 50.0 Hz	
Comparative Tracking Index	100 V	100 V	IEC 60112; IEC/EN 60893-2 6.4
	@Thickness 3.00 mm	@Thickness 0.118 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China