

Elektro-Isola G-Etronax PI Polyimide, Glass Fabric Reinforcement, Dark Brown, Tubes

Category : Polymer , Thermoset , Polyimide, TS

Material Notes:

Description: Extremely good mechanical properties, at high temperatures. Low thermal conductivity. Applications: Material for components used in the aerospace industry. Insulation parts in wire welding guns. Information provided by Elektro-Isola

Order this product through the following link:

http://www.lookpolymers.com/polymer_Elektro-Isola-G-Etronax-PI-Polyimide-Glass-Fabric-Reinforcement-Dark-Brown-Tubes.php

Physical Properties	Metric	English	Comments
Density	1.90 g/cc	0.0686 lb/in ³	24hr/23°C/50% RH; ISO 1183-A; IEC/EN 61212-2 7.3
	@Thickness >=0.000 mm	@Thickness >=0.000 in	
Water Absorption	0.040 %	0.040 %	24hr/50°C+24hr in water at 23°C; ISO 62-1; IEC/EN 61212-2 7.2

Mechanical Properties	Metric	English	Comments
Flexural Strength	380 MPa	55100 psi	24hr/23°C/50% RH; ISO 178; IEC/EN 61212-2 5.1
	@Diameter >=100 mm	@Diameter >=3.94 in	
Compressive Strength	300 MPa	43500 psi	50% RH, Axial; ISO 604; IEC/EN 61212-2 5.2
	@Temperature 23.0 °C, Time 86400 sec	@Temperature 73.4 °F, Time 24.0 hour	
Adhesive Bond Strength	460 MPa	66700 psi	24hr/23°C/50% RH; IEC 60212-2; IEC/EN 61212-2 5.3
	@Diameter <=100 mm	@Diameter <=3.94 in	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Inert	200 °C	392 °F	IEC 60695-11-10; IEC/EN 61212-2 7.1
	@Thickness 3.00 mm, Time 7.20e+7 sec	@Thickness 0.118 in, Time 20000 hour	
Flammability, UL94	V-0	V-0	IEC 60695-11-10; IEC/EN 61212-2 7.4
	@Thickness >=4.00 mm	@Thickness >=0.157 in	

Electrical Properties	Metric	English	Comments
Insulation Resistance	1.00e+9 ohm	1.00e+9 ohm	24hr/50°C+24h in water at 23°C; IEC; IEC/EN 61212-2 6.2
	@Diameter 8.00 - 10.0 mm	@Diameter 0.315 - 0.394 in	
	4.0	4.0	96hr/105°C+1hr/23°C/20%RH; IEC

Dielectric Constant Electrical Properties	Metric @Frequency 50.0 Hz	English @Frequency 50.0 Hz	250° IEC/EN 61212-2 6.3 Comments
Dielectric Strength	10.0 kV/mm	254 kV/in	24hr/23°C/50% RH+1hr/oil 90°C; Perpendicular; IEC 60243-1; IEC/EN 61212-2 6.1.2.1
	@Thickness 3.00 mm	@Thickness 0.118 in	
	2.80 kV/mm	71.1 kV/in	24hr/23°C/50% RH+1hr/oil 90°C; Parallel; IEC 60243-1; IEC/EN 61212- 2 6.1.2.1
	@Diameter >=3.00 mm	@Diameter >=0.118 in	
Dissipation Factor	0.010	0.010	96hr/105°C+1hr/23°C/20%RH; IEC 250; IEC/EN 61212-2 6.3
	@Frequency 50.0 Hz	@Frequency 50.0 Hz	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China